## Pressure and temperature dependence of the Ce valence and *c*-*f* hybridization gap in $CeT_2In_5$ (T = Co, Rh, Ir) heavy-fermion superconductors

H. Yamaoka,<sup>1,\*</sup> Y. Yamamoto,<sup>2</sup> E. F. Schwier,<sup>3</sup> F. Honda,<sup>4</sup> Y. Zekko,<sup>2,†</sup> Y. Ohta,<sup>2,‡</sup> J.-F. Lin,<sup>5,6</sup> M. Nakatake,<sup>3,§</sup>

H. Iwasawa,<sup>3</sup> M. Arita,<sup>3</sup> K. Shimada,<sup>3</sup> N. Hiraoka,<sup>7</sup> H. Ishii,<sup>7</sup> K.-D. Tsuei,<sup>7</sup> and J. Mizuki<sup>2</sup>

<sup>1</sup>RIKEN SPring-8 Center, Sayo, Hyogo 679-5148, Japan

<sup>2</sup>Graduate School of Science and Technology, Kwansei Gakuin University, Sanda, Hyogo 669-1337, Japan

<sup>3</sup>Hiroshima Synchrotron Radiation Center, Hiroshima University, Higashi-Hiroshima, Hiroshima 739-0046, Japan

<sup>4</sup>Institute for Materials Research, Tohoku University, Oarai, Ibaraki 311-1313, Japan

<sup>5</sup>Department of Geological Sciences, The University of Texas at Austin, Austin, Texas 78712, USA

<sup>6</sup>Center for High Pressure Science and Technology Advanced Research (HPSTAR), Shanghai 201203, China

<sup>7</sup>National Synchrotron Radiation Research Center, Hsinchu 30076, Taiwan, Republic of China

(Received 3 September 2015; published 7 December 2015)

Pressure- and temperature-induced changes in the Ce valence and c-f hybridization of the Ce115 superconductors have been studied systematically. Resonant x-ray-emission spectroscopy indicated that the increase of the Ce valence with pressure was significant for CeCoIn<sub>5</sub>, and moderate for CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub>. We found no abrupt change of the Ce valence in the Kondo regime for CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub>, which suggests that valence fluctuations are unlikely to mediate the superconductivity in this material. X-ray-diffraction results were consistent with the pressure-induced change in the Ce valence. High-resolution photoelectron spectroscopy revealed a temperature-dependent reduction of the spectral intensity at the Fermi level, indicating enhanced c-f hybridization on cooling.

DOI: 10.1103/PhysRevB.92.235110

PACS number(s): 71.27.+a, 74.70.Tx, 75.20.Hr, 79.60.-i

The BCS theory that explains superconductivity (SC) based on Cooper pair formation due to the electron-phonon interaction often fails to describe the SC states observed in heavy-fermion systems. In the case of CePd<sub>2</sub>Si<sub>2</sub>, Cooper pair formation mediated by magnetic spin fluctuations (SF) likely explains the SC state [1]. Heavy-fermion compounds such as CeCu<sub>2</sub>Si<sub>2</sub> and CeCu<sub>2</sub>Ge<sub>2</sub>, on the other hand, are known to show two pressure-induced superconducting regimes SC1 and SC2 [2,3]. Interestingly, the superconducting transition temperature  $(T_c)$  of SC2 is higher than that of SC1. In the SC1 regime, it has been considered that the superconductivity is mediated by the SF. Based on the extended periodic Anderson model with repulsion between f and conduction electrons within a slave-boson mean-field theory [4,5], the valence-fluctuation (VF) mediated superconductivity has been proposed theoretically for the SC2 regime. Candidates of the valence-fluctuation mediated superconductor are  $CeCu_2(Si,Ge)_2$ ,  $\beta$ -YbAlB<sub>4</sub>, and Ce115 (CeIrIn<sub>5</sub>, CeRhIn<sub>5</sub>) [5]. Another scenario for the origin of the SC2 region is the orbital-fluctuation (OF) mediated pairing mechanism in which the c-f hybridization of the excited level plays an important role in the origin of the superconductivity in the system [6,7]. It has been shown experimentally that superconductivity can be induced in the *d*-wave channel of Ce-based materials [3] implying the significance of the *c*-*f* hybridization in the occurrence of the SC state. A pressure dependence of the Ce valence change has been reported for CeCu<sub>2</sub>Si<sub>2</sub> [8]. While the results seemingly do not support the VF-SC scenario, the authors did not deny its viability [8]. These facts motivated us to measure the Ce valence of CeCu<sub>2</sub>Ge<sub>2</sub> (pressure dependence) and Ce(Cu<sub>1-x</sub>Ni<sub>x</sub>)Si<sub>2</sub> (*x* dependence) [9]. However, neither compound exhibited a sudden valence change around the transition to SC2.

In the case of CeCoIn<sub>5</sub>, hole-doping with Cd or Hg (Refs. [10,11]) induced an antiferromagnetic (AFM) ground state, while electron-doping with Sn (Refs. [11,12]) either suppressed  $T_c$  or recovered a Fermi liquid ground state. Among the Ce115 systems, CeCoIn<sub>5</sub> is considered to be located near the quantum critical point (QCP), and the AFM SF-SC scenario is likely. However, the origin of the superconductivity in CeIrIn<sub>5</sub> and CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub> is still under debate [13–17].

In CeIrIn<sub>5</sub>, thermal transport properties observed in a rotating magnetic field [13], NMR measurements [14], and the doping-induced AFM state near the quantum critical point [15] were consistent with the magnetic pairing mechanism. Recent resistivity and heat-capacity measurements of 1% Cd-doped CeIrIn<sub>5</sub> under pressure also showed a common magnetic mechanism [16]. Meanwhile, nuclear quadrupole (NQR) experiments showed a large residual spin-lattice relaxation rate  $1/TT_1$  that behaves linearly well below  $T_c$  as well as a change in the pressure-induced NQR frequency at the superconducting region, pointing to a possible valence change of Ce [17]. The temperature dependence of  $1/TT_1$  showed the same trend for both CeIrIn<sub>5</sub> and Cd-doped CeIrIn<sub>5</sub>. These behaviors can be explained by the VF-SC scenario; however, no direct measurement of the Ce valence in Ce115 under pressure has been reported so far. The origin of superconductivity in CeIrIn<sub>5</sub> and Cd-doped CeIrIn<sub>5</sub> remains an unresolved puzzle.

<sup>\*</sup>Author to whom all correspondence should be addressed: yamaoka@spring8.or.jp

<sup>&</sup>lt;sup>†</sup>Present address: Yokohama R & D Center, Nissin Incorporated, 1-18-2 Hakusan, Midori-ku, Yokohama 226-0006, Japan.

<sup>&</sup>lt;sup>‡</sup>Present address: Department of Physics, Osaka University, 1-3 Yamadaoka, Suita 565-0871, Japan.

<sup>&</sup>lt;sup>§</sup>Present address: Aichi Synchrotron Radiation Center, Seto, Aichi 489-0965, Japan.



FIG. 1. (Color online) (a) and (b) Chemical composition dependence of the PFY-XAS spectra at 15 K. Dotted lines, superposed in (a) and (b) for comparison, correspond to the spectra of CeRhIn<sub>5</sub> and CeIrIn<sub>5</sub>, respectively. (c) and (d) Pressure dependence of the PFY-XAS spectra for CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub> at 15 K and CeCoIn<sub>5</sub> at 16 K. (e) PFY-XAS spectrum (circles) of CeCoIn<sub>5</sub> at 16 K and 10.6 GPa with a fitting curve (red solid line), assumed  $f^2$  (light-green solid line, very weak),  $f^1$  (green solid line), and  $f^0$  (blue solid line) components, and background and other residual components (dashed lines). (f) Change in the Ce valence as a function of *y* for Ce(Rh<sub>1-y</sub>Ir<sub>y</sub>)In<sub>5</sub>. (g) and (h) Pressure dependence of the Ce valence (closed circle) for CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub> and CeCoIn<sub>5</sub>. In (f), (g), and (h), the transition temperatures of the antiferromagnetic order (AF, closed triangle) and superconducting region (SC, closed square) are also shown [17,31,40]. IAF is inhomogeneous AF [17].

The AFM-SF involving f electrons may generate an attractive Cooper pairing interaction in the d-wave channel. Below the Kondo temperature, the c-f hybridization becomes stronger, resulting in the development of the hybridization gap. Further decreases in the temperature may cause the superconducting gap to open below  $T_c$  [18]. Therefore, in the SF mediated superconductors, the c-f hybridization gap correlates with the SC. Signatures of the hybridization gap have been observed by optical spectroscopy [19,20] and scanning tunneling spectroscopy (STM) [21–23]. These results call for direct and bulk sensitive measurements of the c-f hybridization gap formation by low photon energy high-resolution photoelectron spectroscopy (PES).

The purpose of this study is to clarify the pressureand temperature-induced change in the Ce valence and c-fhybridization of the Ce115 superconductors systematically. High-quality single crystals of CeCoIn<sub>5</sub>, Ce(Rh<sub>1-v</sub>Ir<sub>v</sub>)In<sub>5</sub> (y = 0, 0.2, 0.4, 0.6, 0.8, and 1.0), and CeIr $(In_{0.925}Cd_{0.075})_5$ were prepared. Resonant x-ray-emission spectroscopy (RXES) with x-ray-absorption spectroscopy (XAS) in the partial fluorescence mode (PFY-XAS) at the Ce  $L_3$  edge was employed to directly observe small valence changes. The valence transition is often correlated to a change in the unit-cell volume. Therefore, x-ray-diffraction (XRD) measurements were performed under high-pressure conditions. The combination of these results allowed us to make a precise quantitative estimation of the temperature and pressure (T-P) dependences of the valence and its correlation to the volume change. Our results show that neither the Ce valence nor the unit-cell volume exhibit any sudden changes in the observed pressure range, which is incompatible with the VF-SC scenario. PES for CeCoIn<sub>5</sub>,

CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub>, and Ce(Rh<sub>1-y</sub>Ir<sub>y</sub>)In<sub>5</sub> at  $h\nu = 8.37 \text{ eV}$  (Xe I line) and 6.36 eV (Laser) was also performed to directly clarify the temperature dependence of the hybridization gap formation. Note that photoelectrons with a kinetic energy of  $\sim 2 \text{ eV}$  tend to have a longer inelastic mean free path of  $\sim 10 \text{ nm}$  [24,25]. Details regarding the experimental techniques can be found in the Supplemental Material [26].

Figure 1(a) shows the PFY-XAS spectra for CeCoIn<sub>5</sub>, CeIrIn<sub>5</sub>, CeRhIn<sub>5</sub>, and CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>55</sub> at 15 K. The differences among these spectra are very small, indicating a similar Ce valence state in these compounds at ambient pressure. The chemical composition dependence of the PFY-XAS spectra for Ce( $Rh_{1-v}Ir_v$ )In<sub>5</sub> is shown Fig. 1(b). To obtain the mean Ce valence, we evaluated the spectral intensity ratios of the  $f^2$ ,  $f^1$ , and  $f^0$  components in the PFY-XAS spectra [27,28]. Figure 1(c) shows an example of a fit to the CeCoIn<sub>5</sub> PFY-XAS spectrum measured at 16 K and 10.6 GPa. Figure 1(f) shows the y dependence of the mean Ce valence with the transition temperatures to the superconducting  $(T_c)$ and AFM states (AF,  $T_N$ ). No apparent y dependence of the electronic structure and the Ce valence is observed within experimental errors. The absence of the sudden change of the Ce valence at the phase boundary clearly indicates that the VF-SC scenario is not likely for these compounds.

Figures 1(c) and 1(d) show the pressure dependence of the PFY-XAS spectra of CeIr( $In_{0.925}Cd_{0.075}$ )<sub>5</sub> and CeCoIn<sub>5</sub> at low temperatures. In Fig. 1(g), the Ce valence in CeIr( $In_{0.925}Cd_{0.075}$ )<sub>5</sub> does not show significant changes up to 3 GPa, and it gradually increases above 5 GPa. Similar behavior has been observed in other Ce superconductors such as CeIrSi<sub>3</sub> (Ref. [27]) and CePd<sub>2</sub>Si<sub>2</sub> (Ref. [28]). In



FIG. 2. (Color online) Pressure dependence of the lattice constants of *a* (closed circle) and *c* (open circle) for (a) CeCoIn<sub>5</sub>, (b) CeIrIn<sub>5</sub>, and (c) CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub>. Pressure dependence of the volume (closed square) and the ratio of c/a (open square) are shown in (d) CeCoIn<sub>5</sub>, (e) CeIrIn<sub>5</sub>, and (f) CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub>, respectively. In (d), (e), and (f) the superconducting and AFM ranges are also shown, where the vertical full scale corresponds to 4 K [17,31,40].

general, Ce-based systems tend to change from Kondo to valence fluctuation regimes upon increasing pressure, which is well understood based on the single-impurity Anderson model [28,29]. The Ce valence in CeCoIn<sub>5</sub>, on the other hand, increases rapidly to the valence fluctuation region with pressure, as shown in Fig. 1(h). This is reasonably understood because the volume of CeCoIn<sub>5</sub> is already smaller than that of CeIrIn<sub>5</sub> at ambient pressure, and the compressibility of CeCoIn<sub>5</sub> is larger than that of the other two compounds, as shown in Fig. 2.

The Ce valence showed a negligible temperature dependence according to the previous XANES study of CeIr<sub>1-x</sub>Rh<sub>x</sub>In<sub>5</sub> at 20–300 K (Ref. [30]) and our XAS study of Ce122 systems at 9–300 K (Ref. [9]). Although the present high-pressure study has been performed at temperatures higher than  $T_c$ , the previous XANES and XAS results suggest that the Ce valence in Ce115 and Ce122 systems does not have a significant temperature dependence.

Figures 2(a)-2(f) show the pressure dependence of the lattice constants, volume, and the ratio of c/a at room temperature. The lattice constants decrease with pressure monotonically. At ambient pressure, the volume of CeCoIn<sub>5</sub> is the smallest among the compounds while its compressibility is the largest. In the case of CeIrIn<sub>5</sub>, the substitution of 7.5%-Ir for Cd does not show a significant change in the pressure dependence of the volume.

A strong correlation between c/a and  $T_c$  has been suggested [31]. While the volume decreases monotonically in these compounds, the c/a ratio shows the maximum value to be around 5 GPa for CeCoIn<sub>5</sub> and 11 GPa for CeIrIn<sub>5</sub>, which are larger than the superconducting pressure range. The 7.5%-Cddoped sample, on the other hand, has no such peak structure in the ratio of c/a. These compounds showed no structural transition in the measured pressured range, supporting no rapid change in the Ce valence. No difference between the basic crystallographic properties of the c/a ratio and bulk modulus between 300 and 10 K has been reported [32]. Therefore, we assume that the above properties are retained down to low temperatures.

The VF-SC scenario predicted a rapid change in the Ce valence just before the maximum  $T_c$  in the T-P phase diagram [4]. This scenario was expected to explain the superconductivity in CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub> in the SC2 phase [17]. Our results, however, indicate that the Ce valence does not change rapidly as predicted by the VF-SC scenario below 3 GPa within the experimental errors. Therefore, the VF-SC scenario cannot be compatible with the results for CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub>. Note that the SF-SC scenario to explain the transport and thermodynamic properties of CeIrIn<sub>5-x</sub>Hg<sub>x</sub>, CeIrIn<sub>5-x</sub>Sn<sub>x</sub>, and CeIr<sub>1-x</sub>Pt<sub>x</sub>In<sub>5</sub> [15]. Additionally, neutron scattering experiments of CeRhIn<sub>5</sub> showed the magnetic fluctuation and magnons [33,34].

Figures 3(a) and 3(b) show the temperature dependence of the valence-band photoelectron spectra of CeIrIn<sub>5</sub> and CeCoIn<sub>5</sub>, respectively. The corresponding density of states (DOS) is shown in Figs. 3(c) and 3(d), which indicate a reduction of the intensity at the Fermi level ( $E_F$ ) upon cooling, i.e., the formation of the *c*-*f* hybridization gap. The result agrees with the prediction of dynamical mean field theory (DMFT) [35], which also explained the scanning tunneling spectroscopy results [21,22] and the two-channel cotunneling model. The DMFT calculations of CeIrIn<sub>5</sub> also reproduced the temperature dependence of the optical conductivity data [36], where the development of the hybridization gap was suggested. Our measurements show direct proof of the development of the hybridization gap.

The c-f hybridization competes with the magnetic order or spin fluctuation, and thus the hybridized band may be modified partly by the appearance of the superconducting state [18,23]. Interestingly, in angle-resolved PES of CeCoIn<sub>5</sub>



FIG. 3. (Color online) Parts (a) and (b) show the temperature dependences of the valence-band spectra near the Fermi level for CeIrIn<sub>5</sub> and CeCoIn<sub>5</sub>, respectively. Parts (c) and (d) show spectra symmetrized with respect to  $E_F$  to recover the temperature-dependent DOS.

at 1.7 K, the weakest hybridization was found in the highly two-dimensional bands [37]. It should be noted that CeRhIn<sub>5</sub>, which does not show superconductivity at ambient pressure, has weaker c-f hybridization strength than CeIrIn<sub>5</sub> [38]. In Fig. 3, the onset temperatures of the hybridization gap formation are not so different between CeCoIn<sub>5</sub> (44–62 K) and CeIrIn<sub>5</sub> (40–60 K). On the other hand, the electronic specific-heat coefficient of CeCoIn<sub>5</sub> is nearly half that of CeIrIn<sub>5</sub>. The results of both the XAS and the PES did not show a significant difference of the hybridization strength between CeCoIn<sub>5</sub> and CeInIn<sub>5</sub> within the experimental accuracies.

In conclusion, the Ce valence of  $CeIr(In_{0.925}Cd_{0.075})_5$  showed a smooth change with pressure from the Kondo to valence fluctuation regions, suggesting that the VF-SC is not likely. The pressure-induced change in the Ce valence for CeCoIn<sub>5</sub> was larger than that for CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub>, which may correspond to larger compressibility in CeCoIn<sub>5</sub>. The PFY-XAS spectra were similar for CeCoIn<sub>5</sub>, CeIrIn<sub>5</sub>, CeRhIn<sub>5</sub>, and CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub> samples at ambient pressure and at 15 K. The superconductivity easily disappeared at high pressures where the system moves to the valence fluctuation regime with stronger *c*-*f* hybridization. Note that recent nonresonant inelastic x-ray scattering has indicated an absence of the orbital rotation in CeCu<sub>2</sub>Ge<sub>2</sub> [39], which is not compatible with the OF scenario predicted by the theory based

on the DMFT [6]. So far, the SF-SC scenario is compatible with the reported experimental results at least for the Ce115 systems. The XRD study indicated that the volume changed smoothly with pressure and no structural transition existed for CeCoIn<sub>5</sub>, CeIrIn<sub>5</sub>, and CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub>, consistent with the PFY-XAS results. CeCoIn<sub>5</sub> showed the largest compressibility among these compounds. High-resolution PES showed development of the c-f hybridization gap at low temperatures in CeIrIn<sub>5</sub> and CeCoIn<sub>5</sub>.

The experiments were performed at SPring-8 Taiwan beamlines BL12XU and BL12B1 (under SPring-8 Proposals No. 2013B4128, No. 2013B4258, No. 2014A4256, and corresponding NSRRC Proposal No. 2013-3-008) and at HiSOR beamlines BL-1 and BL-9A, and Laser PES station (Proposals No. 13-A-1 and No. 14-A-5) in Hiroshima University. We thank the N-BARD, Hiroshima University for supplying the liquid helium. This work is partly supported by a Grant-in-Aid for Sciencific Research from the Japan Society for the Promotion of Science in Japan (Proposal No. 15K05194). J.F.L. acknowledges support from HPSTAR. E.F.S. acknowledges financial support from the JSPS postdoctoral fellowship for overseas researchers as well as the Alexander von Humboldt Foundation (Grant No. P13783).

- N. D. Mathur, F. M. Grosche, S. R. Julian, I. R. Walker, D. M. Freye, R. K. Haselwimmer, and G. G. Lonzarich, Magnetically mediated superconductivity in heavy fermion compounds, Nature (London) 394, 39 (1998).
- [2] H. Q. Yuan and F. Steglich, Unconventional superconductivity and quantum criticality in pressurized  $CeCu_2(Si_{1-x}Ge_x)_2$ , Physica C 460-462, 141 (2007).

- [3] F. Steglich, C. Geibel, F. M. Grosche, M. Loewenhaupt, O. Stockert, S. Wirth, and H. Q. Yuan, Experimental evidence for unconventional BCS states in heavy-fermion metals, Physica B 403, 968 (2008).
- [4] Y. Onishi and K. Miyake, Enhanced valence fluctuations caused by *f-c* Coulomb interaction in Ce-based heavy electrons: Possible origin of pressure-induced enhancement of superconducting transition temperature in CeCu<sub>2</sub>Ge<sub>2</sub> and related compounds, J. Phys. Soc. Jpn. **69**, 3955 (2000).
- [5] S. Watanabe and K. Miyake, Roles of critical valence fluctuations in Ce- and Yb-based heavy fermion metals, J. Phys.: Condens. Matter 23, 094217 (2011).
- [6] L. V. Pourovskii, P. Hansmann, M. Ferrero, and A. Georges, Theoretical Prediction and Spectroscopic Fingerprints of an Orbital Transition in CeCu<sub>2</sub>Si<sub>2</sub>, Phys. Rev. Lett. **112**, 106407 (2014).
- [7] Z. Ren, L. V. Pourovskii, G. Giriat, G. Lapertot, A. Georges, and D. Jaccard, Giant Overlap Between the Magnetic and Superconducting Phases of CeAu<sub>2</sub>Si<sub>2</sub> Under Pressure, Phys. Rev. X 4, 031055 (2014).
- [8] J.-P. Rueff, S. Raymond, M. Taguchi, M. Sikora, J.-P. Itié, F. Baudelet, D. Braithwaite, G. Knebel, and D. Jaccard, Pressure-Induced Valence Crossover in Superconducting CeCu<sub>2</sub>Si<sub>2</sub>, Phys. Rev. Lett. **106**, 186405 (2011).
- [9] H. Yamaoka, Y. Ikeda, Jarrige, N. Tsujii, Y. Zekko, Y. Yamamoto, J. Mizuki, J.-F. Lin, N. Hiraoka, H. Ishii, K.-D. Tsuei, T. C. Kobayashi, F. Honda, and Y. Ōnuki, Role of Valence Fluctuations in the Superconductivity of Ce122 Compound, Phys. Rev. Lett. **113**, 086403 (2014).
- [10] L. D. Pham, T. Park, S. Maquilon, J. D. Thompson, and Z. Fisk, Reversible Tuning of the Heavy-Fermion Ground State in CeCoIn<sub>5</sub>, Phys. Rev. Lett. **97**, 056404 (2006).
- [11] K. Gofryk, F. Ronning, J.-X. Zhu, M. N. Ou, P. H. Tobash, S. S. Stoyko, X. Lu, A. Mar, T. Park, E. D. Bauer, J. D. Thompson, and Z. Fisk, Electronic Tuning and Uniform Superconductivity in CeCoIn<sub>5</sub>, Phys. Rev. Lett. **109**, 186402 (2012).
- [12] S. M. Ramos, M. B. Fontes, E. N. Hering, M. A. Continentino, E. Baggio-Saitovich, F. Dinóla Neto, E. M. Bittar, P. G. Pagliuso, E. D. Bauer, J. L. Sarrao, and J. D. Thompson, Superconducting Quantum Critical Point in CeCoIn<sub>5-x</sub>Sn<sub>x</sub>, Phys. Rev. Lett. 105, 126401 (2010).
- [13] Y. Kasahara, T. Iwasawa, Y. Shimizu, H. Shishido, T. Shibauchi, I. Vekhter, and Y. Matsuda, Thermal Conductivity Evidence for a  $d_{x^2-y^2}$  Pairing Symmetry in the Heavy-Fermion CeIrIn<sub>5</sub> Superconductor, Phys. Rev. Lett. **100**, 207003 (2008).
- [14] S. Kambe, H. Sakai, Y. Tokunaga, and R. E. Walstedt, Quantum critical behavior in heavy-fermion superconductor CeIrIn<sub>5</sub>, Phys. Rev. B 82, 144503 (2010).
- [15] T. Shang, R. E. Baumbach, K. Gofryk, F. Ronning, Z. F. Weng, J. L. Zhang, X. Lu, E. D. Bauer, J. D. Thompson, and H. Q. Yuan, CeIrIn<sub>5</sub>: Superconductivity on a magnetic instability, Phys. Rev. B 89, 041101 (2014).
- [16] Y. Chen, W. B. Jiang, C. Y. Guo, F. Ronning, E. D. Bauer, T. Park, H. Q. Yuan, Z. Fisk, J. D. Thompson, and X. Lu, Reemergent Superconductivity and Avoided Quantum Criticality in Cd-Doped CeIrIn<sub>5</sub> Under Pressure, Phys. Rev. Lett. **114**, 146403 (2015).
- [17] M. Yashima, N. Tagami, S. Taniguchi, T. Unemori, K. Uematsu, H. Mukuda, Y. Kitaoka, Y. Ōta, F. Honda, R. Settai, and Y. Ōnuki,

Possibility of Valence-Fluctuation-Mediated Superconductivity in Cd-Doped CeIrIn<sub>5</sub> probed by In NQR, Phys. Rev. Lett. **109**, 117001 (2012).

- [18] J. S. Van Dyke, F. Massee, M. P. Allan, J. C. S. Davis, C. Petrovic, and D. K. Morr, Direct evidence for a magnetic *f*-electron-mediated pairing mechanism of heavy-fermion superconductivity in CeCoIn<sub>5</sub>, Proc. Natl. Acad. Sci. (USA) 111, 11663 (2014).
- [19] F. P. Mena, D. van der Marel, and J. L. Sarrao, Optical conductivity of  $CeMIn_5$  (M = Co, Rh, Ir), Phys. Rev. B 72, 045119 (2005).
- [20] K. S. Burch, S. V. Dordevic, F. P. Mena, A. B. Kuzmenko, D. van der Marel, J. L. Sarrao, J. R. Jeffries, E. D. Bauer, M. B. Maple, and D. N. Basov, Optical signatures of momentum-dependent hybridization of the local moments and conduction electrons in Kondo lattices, Phys. Rev. B 75, 054523 (2007).
- [21] P. Aynajian, E. H. da Silva Neto1, A. Gyenis, R. E. Baumbach, J. D. Thompson, Z. Fisk, E. D. Bauer, and A. Yazdani, Visualizing heavy fermions emerging in a quantum critical Kondo lattice, Nature (London) 486, 201 (2012).
- [22] M. P. Allan, F. Massee, D. K. Morr, J. Van Dyke, A. W. Rost, A. P. Mackenzie, C. Petrovic, and J. C. Davis, Imaging Cooper pairing of heavy fermions in CeCoIn<sub>5</sub>, Nat. Phys. 9, 468 (2013).
- [23] B. B. Zhou, S. Misra, E. H. da Silva Neto, P. Aynajian, R. E. Baumbach, J. D. Thompson, E. D. Bauer, and A. Yazdani, Visualizing nodal heavy fermion superconductivity in CeCoIn<sub>5</sub>, Nat. Phys. 9, 474 (2013).
- [24] C. R. Brundle, The application of electron spectroscopy to surface studies, J. Vac. Sci. Technol. 11, 212 (1974).
- [25] M. P. Seah and W. A. Dench, Quantitative electron spectroscopy of surfaces: A standard data base for electron inelastic mean free paths in solids, Surf. Interf. Anal. 1, 2 (1979).
- [26] See Supplemental Material at http://link.aps.org/supplemental/ 10.1103/PhysRevB.92.235110, which includes Refs. [41–46]. Details of the experiments, the Ce 4*d*-4*f* PES, the fits of the pressure-volume relation, and the RXES spectra for CeIr(In<sub>0.925</sub>Cd<sub>0.075</sub>)<sub>5</sub> are described.
- [27] H. Yamaoka, A. Kotani, Y. Kubozono, A. M. Vlaicu, H. Oohashi, T. Tochio, Y. Ito, and H. Yoshikawa, Pressure and temperature dependences of the electronic structure of CeIrSi<sub>3</sub> probed by resonant x-ray emission spectroscopy, J. Phys. Soc. Jpn. 80, 014702 (2011).
- [28] H. Yamaoka, Y. Zekko, A. Kotani, I. Jarrige, N. Tsujii, J.-F. Lin, J. Mizuki, H. Abe, H. Kitazawa, N. Hiraoka, H. Ishii, and K.-D. Tsuei, Electronic transitions in CePd<sub>2</sub>Si<sub>2</sub> studied by resonant x-ray emission spectroscopy at high pressures and low temperatures, Phys. Rev. B 86, 235131 (2012).
- [29] A. Kotani and H. Yamaoka, Final-state interaction in the L<sub>3</sub> x-ray absorption spectra of mixed-valence Ce and Yb compounds, J. Phys. Soc. Jpn. 84, 033702 (2015).
- [30] M. Daniel, S.-W. Han, C. H. Booth, A. L. Cornelius, P. G. Pagliuso, J. L. Sarrao, and J. D. Thompson, X-ray absorption studies of the local structure and *f*-level occupancy in CeIr<sub>1-x</sub>Rh<sub>x</sub>In<sub>5</sub>, Phys. Rev. B **71**, 054417 (2005).
- [31] P. G. Pagliuso, R. Movshovich, A. D. Bianchi, M. Nicklas, N. O. Moreno, J. D. Thompson, M. F. Hundley, J. L. Sarrao, and Z. Fisk, Multiple phase transitions in Ce(Rh,Ir,Co)In<sub>5</sub>, Physica B **312-313**, 129 (2002).
- [32] R. S. Kumar, H. Kohlmann, B. E. Light, A. L. Corneliu, V. Raghavan, T. W. Darling, and J. L. Sarrao, Anisotropic

elastic properties of CeRhIn<sub>5</sub>, Phys. Rev. B **69**, 014515 (2004).

- [33] P. Das, S.-Z. Lin, N. J. Ghimire, K. Huang, F. Ronning, E. D. Bauer, J. D. Thompson, C. D. Batista, G. Ehlers, and M. Janoschek, Magnitude of the Magnetic Exchange Interaction in the Heavy-Fermion Antiferromagnet CeRhIn<sub>5</sub>, Phys. Rev. Lett. 113, 246403 (2014).
- [34] C. Stock, J. A. Rodriguez-Rivera, K. Schmalzl, E. E. Rodriguez, A. Stunault, and C. Petrovic, Single to Multiquasiparticle Excitations in the Itinerant Helical Magnet CeRhIn<sub>5</sub>, Phys. Rev. Lett. **114**, 247005 (2015).
- [35] R. Peters and N. Kawakami, Surface density of states of layered *f*-electron materials, Phys. Rev. B 89, 041106(R) (2014).
- [36] J. H. Shim, K. Haule, and G. Kotliar, Modeling the localizedto-itinerant electronic transition in the heavy fermion system CeIrIn<sub>5</sub>, Science **318**, 1615 (2007).
- [37] A. Koitzsch, T. K. Kim, U. Treske, M. Knupfer, B. Büchner, M. Richter, I. Opahle, R. Follath, E. D. Bauer, and J. L. Sarrao, Band-dependent emergence of heavy quasiparticles in CeCoIn<sub>5</sub>, Phys. Rev. B 88, 035124 (2013).
- [38] S. Fujimori, A. Fujimori, K. Shimada, T. Narimura, K. Kobayashi, H. Namatame, M. Taniguchi, H. Harima, H. Shishido, S. Ikeda, D. Aoki, Y. Tokiwa, Y. Haga, and Y. Onuki, Direct observation of a quasiparticle band in CeIrIn<sub>5</sub>: An angle-resolved photoemission spectroscopy study, Phys. Rev. B 73, 224517 (2006).
- [39] J.-P. Rueff, J. M. Ablett, F. Strigari, M. Deppe, M. W. Haverkort, L. H. Tjeng, and A. Severing, Absence of orbital rotation

in superconducting  $CeCu_2Ge_2$ , Phys. Rev. B **91**, 201108(R) (2015).

- [40] V. A. Sidorov, M. Nicklas, P. G. Pagliuso, J. L. Sarrao, Y. Bang, A. V. Balatsky, and J. D. Thompson, Superconductivity and Quantum Criticality in CeCoIn<sub>5</sub>, Phys. Rev. Lett. 89, 157004 (2002).
- [41] Y. Feng, R. Jaramillo, J. Wang, Y. Ren, and T. F. Rosenbaum, Invited Article: High-pressure techniques for condensed matter physics at low temperature, Rev. Sci. Instrum. 81, 041301 (2010).
- [42] H. Yamaoka, Y. Zekko, I. Jarrige, J.-F. Lin, N. Hiraoka, H. Ishii, K.-D. Tsuei, and J. Mizuki, Ruby pressure scale in a lowtemperature diamond anvil cell, J. Appl. Phys. **112**, 124503 (2012).
- [43] K. Shimada, K. Kobayashi, T. Narimura, P. Baltzer, H. Namatame, M. Taniguchi, T. Suemitsu, T. Sasakawa, and T. Takabatake, Direct observation of the Ce 4*f* states in the Kondo semiconductor CeRhAs and related compounds: A high-resolution resonant photoemission study, Phys. Rev. B 66, 155202 (2002).
- [44] F. Izumi and K. Momma, Three-dimensional visualization in powder diffraction, Solid State Phenom. 130, 15 (2007).
- [45] N. F. Brady, J. M. Montgomery, G. Tsoi, T. Gebre, S. T. Weir, Y. K. Vohra, and D. J. Hilton, Equation of state and electrical resistivity of the heavy fermion superconductor CeCoIn<sub>5</sub> to 51 GPa, Eur. Phys. J. B 86, 334 (2013).
- [46] R. Kumar, A. Cornelius, and J. Sarrao, Compressibility of CeMIn<sub>5</sub> and Ce<sub>2</sub>MIn<sub>8</sub> (M = Rh, Ir, and Co) compounds, Phys. Rev. B **70**, 214526 (2004).